



UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

Address: COMMISSIONER FOR PATENTS

P.O. Box 1450

Alexandria, Virginia 22313-1450

www.uspto.gov

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
10/524,546	11/01/2005	Kenichiro Nakajima	Q71952	1419
23373 7590 12/26/2008 SUGHRUE MION, PLLC 2100 PENNSYLVANIA AVENUE, N.W. SUITE 800 WASHINGTON, DC 20037			EXAMINER GARDNER, SHANNON M	
			ART UNIT	PAPER NUMBER
			1795	
			MAIL DATE	DELIVERY MODE
			12/26/2008	PAPER

Please find below and/or attached an Office communication concerning this application or proceeding.

The time period for reply, if any, is set in the attached communication.

Office Action Summary

Application No.

10/524,546

Applicant(s)

NAKAJIMA, KENICHIRO

Examiner

Shannon Gardner

Art Unit

1795

-- The MAILING DATE of this communication appears on the cover sheet with the correspondence address --
Period for Reply

A SHORTENED STATUTORY PERIOD FOR REPLY IS SET TO EXPIRE 3 MONTH(S) OR THIRTY (30) DAYS, WHICHEVER IS LONGER, FROM THE MAILING DATE OF THIS COMMUNICATION.

- Extensions of time may be available under the provisions of 37 CFR 1.136(a). In no event, however, may a reply be timely filed after SIX (6) MONTHS from the mailing date of this communication.
- If NO period for reply is specified above, the maximum statutory period will apply and will expire SIX (6) MONTHS from the mailing date of this communication.
- Failure to reply within the set or extended period for reply will, by statute, cause the application to become ABANDONED (35 U.S.C. § 133). Any reply received by the Office later than three months after the mailing date of this communication, even if timely filed, may reduce any earned patent term adjustment. See 37 CFR 1.704(b).

Status

- 1) ☒ Responsive to communication(s) filed on 17 October 2008 (Applicant Arguments).
- 2a) ☐ This action is **FINAL**. 2b) ☒ This action is non-final.
- 3) ☐ Since this application is in condition for allowance except for formal matters, prosecution as to the merits is closed in accordance with the practice under *Ex parte Quayle*, 1935 C.D. 11, 453 O.G. 213.

Disposition of Claims

- 4) ☒ Claim(s) 1 and 3-8 is/are pending in the application.
- 4a) Of the above claim(s) _____ is/are withdrawn from consideration.
- 5) ☐ Claim(s) _____ is/are allowed.
- 6) ☐ Claim(s) _____ is/are rejected.
- 7) ☐ Claim(s) _____ is/are objected to.
- 8) ☐ Claim(s) _____ are subject to restriction and/or election requirement.

Application Papers

- 9) ☐ The specification is objected to by the Examiner.
- 10) ☐ The drawing(s) filed on _____ is/are: a) ☐ accepted or b) ☐ objected to by the Examiner.
Applicant may not request that any objection to the drawing(s) be held in abeyance. See 37 CFR 1.85(a).
Replacement drawing sheet(s) including the correction is required if the drawing(s) is objected to. See 37 CFR 1.121(d).
- 11) ☐ The oath or declaration is objected to by the Examiner. Note the attached Office Action or form PTO-152.

Priority under 35 U.S.C. § 119

- 12) ☐ Acknowledgment is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d) or (f).
- a) ☐ All b) ☐ Some * c) ☐ None of:
1. ☐ Certified copies of the priority documents have been received.
 2. ☐ Certified copies of the priority documents have been received in Application No. _____.
 3. ☐ Copies of the certified copies of the priority documents have been received in this National Stage application from the International Bureau (PCT Rule 17.2(a)).

* See the attached detailed Office action for a list of the certified copies not received.

Attachment(s)

- 1) ☒ Notice of References Cited (PTO-892)
- 2) ☐ Notice of Draftsperson's Patent Drawing Review (PTO-948)
- 3) ☒ Information Disclosure Statement(s) (PTO/S5108)
Paper No(s)/Mail Date 7/10/2008
- 4) ☐ Interview Summary (PTO-413)
Paper No(s)/Mail Date _____
- 5) ☐ Notice of Informal Patent Application
- 6) ☐ Other: _____

DETAILED ACTION

Response to Amendment

Applicant's amendment of 10/17/2008 does not render the application allowable.

Remarks

Applicant has cancelled claims 2 and 9-10 and amended claims 1, 3, and 6. Currently claims 1 and 3-8 are pending in the application and are considered on their merits below.

Status of Objections and Rejections

The rejection of claims 2 and 9-10 under 35 U.S.C 112, second paragraph is obviated by Applicant's cancellation.

The rejection of claim 6 under 35 U.S.C 112, second paragraph is withdrawn in view of Applicant's amendment.

The double patenting rejection of claims 1-10 is withdrawn in view of Applicant's Terminal Disclaimer.

All other rejections from the previous office action are withdrawn in view of Applicant's arguments which are considered to be persuasive. New grounds of rejection are set forth below.

Claim Rejections - 35 USC § 103

1. The following is a quotation of 35 U.S.C. 103(a) which forms the basis for all obviousness rejections set forth in this Office action:

(a) A patent may not be obtained though the invention is not identically disclosed or described as set forth in section 102 of this title, if the differences between the subject matter sought to be patented and the prior art are such that the subject matter as a whole would have been obvious at the time the invention was made to a person having ordinary skill in the art to which said subject matter pertains. Patentability shall not be negated by the manner in which the invention was made.

2. The factual inquiries set forth in *Graham v. John Deere Co.*, 383 U.S. 1, 148 USPQ 459 (1966), that are applied for establishing a background for determining obviousness under 35 U.S.C. 103(a) are summarized as follows:

1. Determining the scope and contents of the prior art.
2. Ascertaining the differences between the prior art and the claims at issue.
3. Resolving the level of ordinary skill in the pertinent art.
4. Considering objective evidence present in the application indicating obviousness or nonobviousness.

3. Claims 1, 4, 5, 6, and 8 are rejected under 35 U.S.C. 103(a) as being unpatentable over Kitagawa et al. (*Microstructures and Thermoelectric Properties of $(\text{FeSb}_3)_{1-x}\text{La}_x$ Ribbons*) in view of Lange (*Lange's Handbook of Chemistry, Table 3.2*) and Knosp et al. (US 20020037453).

As to claim 1, Kitagawa is directed to a method for producing a filled skutterudite-based alloy (pp 334; 1st column, **abstract**), comprising:

- melting alloy raw material of La, Fe and Sb to form a melt (pp 334; 1st column, **abstract** and 2nd column, 1st paragraph); and
- Rapidly quenching the melt to form a solidified product (pp 334; 1st column, 3rd paragraph and 2nd column, 1st paragraph).

Though Kitagawa teaches that the alloy raw material is melted in a high frequency induction furnace (pp 334; 2nd column, 1st paragraph) and rapidly solidified via strip casting on a copper roll (pp 334; 2nd column, 1st paragraph) but is silent as to melting the raw material at a temperature of 800 to 1,800 °C and as to quenching the melt at a cooling rate of 5×10^2 to 3×10^3 °C/second through strip casting.

However, Kitagawa teaches that pure Fe, Sb and La were weighed and melted together (pp 334; 2nd column, 1st paragraph). The melting points of Fe, Sb and La are 1535 °C, 630.7 °C, and 920 °C, respectively (see Lange's Handbook). A skilled artisan would appreciate that the three metals would be heated to a minimum temperature of 1535 °C to ensure complete melting of the metals.

Therefore, it would have been obvious to one of ordinary skill in the art at the time of the invention to heat the metals of Kitagawa to at least 1535 °C, as this temperature allows for sufficient melting, and therefore mixing of the three metals present in the alloy and allow one skilled in the art to obtain the desired metal composition.

Further, Knosp teaches an alloy comprising a rare earth metal, a transition metal, and metallic antimony (paragraph [0009]) that is melted and rapidly cooled using either a melt spinning process or strip casting [emphasis added] at a cooling rate of 10 °C/second to 10⁶°C/second (paragraphs [0034] and [0036]).

Therefore, a skilled artisan would recognize that the rapid quenching of the melt by a spin process or strip casting would be obvious to try over one another with a reasonable expectation of success (see MPEP § 2141(III)). The Examiner notes that in the case where claimed ranges "overlap or lie inside ranges disclosed by the prior art" a *prima facie* case of obviousness exists (*In re Wertheim* and MPEP § 2144.05(I)).

Regarding claim 4, modified Kitagawa teaches the solidified product comprising alloy strips having a thickness of 0.1mm (Knosp; paragraph [0036]). The Examiner notes that in the case where claimed ranges "overlap or lie inside ranges disclosed by

the prior art" a *prima facie* case of obviousness exists (*In re Wertheim* and MPEP § 2144.05(I)).

Regarding claim 5, modified Kitagawa teaches that the skutterudite-based alloy contains a filled skutterudite phase in an amount of 100 mass% (Kitagawa; pp 335, 2nd column, 1st paragraph and Figure 5). The Examiner notes that even though product-by-process claims are limited by and defined by the process, determination of patentability is based on the product itself (MPEP § 2113).

Regarding claim 6, modified Kitagawa teaches a filled skutterudite phase in an amount of at least 95 vol. % (Kitagawa; pp. 335, 2:9 and Fig. 5) and a phase, other than the filled skutterudite phase, having a maximum grain diameter of 10 μm or less (Kitagawa; Fig. 2, Fig. 3 and p. 335, 2:16-20). The examiner notes that even though product-by-process claims are limited by and defined by the process, determination of patentability is based on the product itself (see MPEP § 2113).

Regarding claim 8, modified Kitagawa teaches a thermoelectric element fabricated using the filled skutterudite-based alloy (pp 335, 1st column, 1st paragraph).

4. Claim 3 is rejected under 35 U.S.C. 103(a) as being unpatentable over Kitagawa et al. (*Microstructures and Thermoelectric Properties of $(\text{FeSb}_3)_{1-x}\text{La}_x$ Ribbons*) in view of Lange (*Lange's Handbook of Chemistry, Table 3.2*) and Knosp et al. (US 20020037453) as applied to claim 1 above, and further in view of Hehmann et al. (WO199604409).

Regarding claim 3, Applicant is directed above for a full discussion of Kitagawa in view of Lange and Knosp as applied to claim 1. Modified Kitagawa teaches that the

alloy raw material is melting in an inert gas atmosphere (argon atmosphere) (Kitagawa; pp 334, 2nd column, 1st paragraph), but is silent as to the specific atmospheric pressure.

However, it is known in the rare earth metal alloy art that melting the alloy raw material in an inert atmosphere (Ar) at a highest possible atmospheric pressure minimizes losses of the melt due to evaporation, as taught by Hehmann (pp 31, section 1.1.2).

One reading the Kitagawa as a whole would understand that the reference is not concerned with a particular pressure of the argon atmosphere and therefore selection of a particular pressure would have been within purview of one of ordinary skill in the art. Further, it would have been obvious to one of ordinary skill in the art at the time of the invention to melt the alloy raw material at a pressure higher than 0.1MPa and not higher than 0.2MPa, to minimize losses of the melt due to evaporation, as taught by Hehmann (also see MPEP § 2141 (III)).

5. Claim 7 is rejected under 35 U.S.C. 103(a) as being unpatentable over Kitagawa et al. (*Microstructures and Thermoelectric Properties of (FeSb₃)_{1-x}La_x Ribbons*) in view of Lange (*Lange's Handbook of Chemistry, Table 3.2*) and Knosp et al. (US 20020037453) as applied to claim 5 above, and further in view of Hirota et al. (US 6322637).

Regarding claim 7, Applicant is directed above for a full discussion of Kitagawa in view of Lange and Knosp as applied to claim 5. Modified Kitagawa teaches the percentage of atoms in the metal alloy ribbons are 100% LaFe₂Sb₁₂ (Kitagawa; pp 335, 2nd column, 1st paragraph) and that the individual metals were melted in an inert

atmosphere (Ar) (Kitagawa; pp 334, 2nd column, first paragraph), but is silent as to the filled-skutterudite based alloy containing oxygen, nitrogen and carbon in a total amount of 0.2 mass% of less.

However, it is known in the rare earth metal alloy art to create such alloys with impurities in a total amount of 0.2 mass% or less, as taught by Hirota (column 2, line 6 to column 3, line 7) to achieve desired design characteristics.

Therefore, it would have been obvious to one of ordinary skill in the art at the time of the invention to keep the oxygen, nitrogen and carbon content of modified Kitagawa's alloy 0.2 mass% or less, as taught by Hirota to achieve desired design characteristics.

Response to Arguments

6. Applicant's arguments with respect to claim 2 have been considered but are moot in view of Applicant's cancellation.

7. Applicant's arguments, see pp 5-9 of Arguments, filed 10/6/2008, with respect to the rejection(s) of claim(s) 1, 3, 4, and 7 under 35 U.S.C 102 and 103 have been fully considered and are persuasive. Therefore, the rejection has been withdrawn. However, upon further consideration, a new ground(s) of rejection is made in view of Knosp, Hehmann and Hirota.

Contact/Correspondence Information

Any inquiry concerning this communication or earlier communications from the examiner should be directed to Shannon Gardner whose telephone number is

(571)270-5270. The examiner can normally be reached on Monday to Thursday, 8am-5pm EST.

If attempts to reach the examiner by telephone are unsuccessful, the examiner's supervisor, Alexa Neckel can be reached on 571.272.1446. The fax phone number for the organization where this application or proceeding is assigned is 571-273-8300.

Information regarding the status of an application may be obtained from the Patent Application Information Retrieval (PAIR) system. Status information for published applications may be obtained from either Private PAIR or Public PAIR. Status information for unpublished applications is available through Private PAIR only. For more information about the PAIR system, see <http://pair-direct.uspto.gov>. Should you have questions on access to the Private PAIR system, contact the Electronic Business Center (EBC) at 866-217-9197 (toll-free). If you would like assistance from a USPTO Customer Service Representative or access to the automated information system, call 800-786-9199 (IN USA OR CANADA) or 571-272-1000.

/S. G./
Examiner, Art Unit 1795

/Alexa D. Neckel/
Supervisory Patent Examiner, Art Unit 1795